

## **Cement compatible**

- ▶ Free of ammonia odor
- ▶ Due to its low MFFT, addition of plasticizer and coalescent agent is not required
- Alkali stable
- ▶ UV resistance
- ► Flexibility at low temperatures to comply with the European Norms (EN 14891 crack bridging at -20 C and -5 C)

## Areas of use:

- ▶ 2K-1K Flexible Hydroinsulation Systems
- Flexible coatings
- Facade reinforcement systems and resin-bound plasters



Product	Solid Content %	рН	Viscosity, cPs	Tg (°C)	MFFT (°C)
TECOSIT AC 5185	57±2,0	7,0-9,0	1000-3000	-10	0
TECOSIT AC 5250	52±2,0	7,0-9,0	800-2000	-30	0



